Kenoran Sage

Granite

Kenoran Sage granite blocks are available in impressive sizes, making them an ideal choice for large-scale architectural projects.



Type of Stone	Granite		
Source	Kenora, Ontario, Canada		
Available Finishes	Polished, Honed, Antique, Flamed, Sandblasted, Waterjet, Bush Hammered, Axed, Combed, Smooth, Stipple, Rock Face		
	ASTM	**Imperial**	**Metric**
Absorption by Weight	ASTM C97	0.17%	0.17%
Density	ASTM C97	166.8 lb/ft^3	2 671.88 kg/m^3
Compressive Strength	ASTM C170	19 401 psi	133.77 MPa
Modulus of Rupture	ASTM C99	2 040 psi	14.07 MPa

t. 1 (418) 831-4422
info@technoprofil.ca
www.technoprofil.ca

TECHNOPROFIL

Finishes

Different finishes have an impact on the stone’s texture and color. Techniques such as flamed or waterjet finishes enhance the stone's natural grains, adding distinct texture and depth.
Several other finishes are available. The Technoprofil team has the expertise to advise you on the finishes best suited to your projects.


Polished

t. 1 (418) 831-4422
info@technoprofil.ca
www.technoprofil.ca

TECHNOPROFIL